

# TOUGH PLA

TOUGH PLA is engineered for its **high impact** and strength like ABS and the stiffness of PLA. The material shows excellent results in layer adhesion and is the perfect match for tooling or manufacturing aids where a high impact is needed. TOUGH PLA is a plug & play material and printable on a wide range of temperatures.


## Material features:

- High impact and stiffness
- Prints like regular PLA – easy to print
- Printable with various print temperatures
- Suitable for applications which needs to be strong
- Industrial touch and feel



## Colours:

TOUGH PLA is available in 6 colours.



## Packaging:

TOUGH PLA is available in nearly any type of packaging and labelling. Ask our team to help you customizing your product.

### Filament specs.

Size	Ø tolerance	Roundness
1,75mm	± 0,05mm	≥ 95%
2,85mm	± 0,10mm	≥ 95%

### Material properties

Description	Testmethod	Typical value
Specific gravity	ISO 1183	1,21 g/cc
MFR 210°C/2,16 kg	ISO 1133	8,75 gr/10 min
Tensile strength at yield	ISO 527	46 MPa
Tensile strength at Break	ISO 527	19 MPa
Strain at yield	ISO 527	2%
Strain at break	ISO 527	27%
Tensile Modulus	ISO 527	2750 MPa
Impact strength - Charpy method 23°C	ISO 179	29,8 kJ/m2
Vicat softening temperature B	ISO 306	55°C
Printing temp.	Internal Method	210±10°C

## Additional info:

Recommended temperature for heated bed is ± 60-80°C. Adhesion is possible on different surfaces. TOUGH PLA can be used on all common desktop FDM or FFF technology 3D printers.

Storage: Cool and dry (15-25°C) and away from UV light. This enhances the shelf life significantly.

# Mechanical Specifications

During additional research, a print profile has been made which was optimized for achieving the best performance on printed parts. Table 1 shows the typical values of an injection moulded specimen compared to a 3D-printed specimen in both the X-Y axis (3D-printed horizontally) and the Z-axis (3D-printed vertically).

**Table 1: Data of both injection moulded and 3D-printed specimens.\***

	Injection Moulded	3D-Printed X-Y	3D-Printed Z
Young's Modulus [MPa] ISO 527	2750	2450	2200
Stress at Yield [MPa] ISO 527	46	41	33
Stress at Break [MPa] ISO 527	19	32	33
Strain at Yield [%] ISO 527	2	2	2
Strain at Break [%] ISO 527	27	20	2,6
Charpy Impact (Kj/m2) ISO 179	29,8	22,9	2,2
Flexural Strength ISO 178	2750	2700	2250
Flexural Modulus ISO 178	72	76	60



**TOUGH PLA has excellent impact properties at a brought range of temperatures.**

### Print Conditions

All specimens have been printed using a 0.4mm nozzle and the layer height was set to 0.2mm. The room in which the 3D-printer was located had an environmental temperature of  $\pm 25^{\circ}\text{C}$ .

### \*Test Conditions

The tensile tests have been carried out according to ISO-527 using modified 1BA specimens (3D-printing) and 1A specimens (injection moulding). The room in which the Universal Testing Machine was located had an environmental temperature of  $\pm 20^{\circ}\text{C}$ .

MCPN Netherlands B.V. cannot be held responsible for any inaccuracies. No guarantees can be given since differences in data could be caused by differences between individual 3D-printers.